

Custom Colors Available Upon Request

SITE CONSTRUCTION
CONCRETE
FINISHES

2,3,9

5/07
BOMANITE CORPORATION

COLOR SELECTION GUIDE

NOTE: Color selections on this chart approximate as closely as possible the appearance of integral color when used on horizontal troweled concrete. Variations can be expected due to job site conditions, finishing techniques, use of sealers and slight raw material color drifts. Consistency of color of cement and aggregates as well as the content of the concrete mix design is critical in achieving uniform color from batch to batch. 4" to 5" slumps are recommended. Higher slumps should be achieved by using water reducing or plasticizing admixtures, NOT by adding water. The addition of extra water to the mix will affect the uniformity of the color. Uneven curing and/or rapid drying of the concrete will also affect the uniformity of the color.



BAY GREEN 5A




COAL GRAY 4A



THISTLE BROWN 4B



APRICOT 4C



RED CLAY 4D



GOLDENROD 4E



PAPRIKA 4F



MAIZE 4G



SIENNA 3A



GUNMETAL GRAY 3B



GRANOLA 3C



CORNSTALK 3D



MIST GREEN 3E



CAMEL 2A



SALMON 2B



COOL MAUVE 2C



SUNSET 2D



LIGHT COPPER 1A



SEAL GRAY 1B



LIGHT MELON 1C



RHUBARB 1D



BUCKSKIN 1E



QUAIL GRAY 1F



SIERRA ROSE 1G



CHAMOIS 1H